



Thickness Tolerances: Coil and Cut Length Sheets

Gauge	Decimal	Hot Rolled, P & O	Cold Rolled	Lbs. Per
		Tolerance Range	Tolerance Range	Sq. Ft.
7	0.1793	.1713 to .1873	7.5
8	0.1644	.1564 to .1724	6.875
9	0.1495	.1415 to .1575	6.25
10	0.1345	.1265 to .1425	.1285 to .1405	5.625
11	0.1196	.1116 to .1276	.1136 to .1256	5
12	0.1046	.0966 to .1126	.0986 to .1106	4.375
13	0.0897	.0827 to .0967	.0847 to .0947	3.75
14	0.0747	.0677 to .0817	.0697 to .0797	3.125
15	0.0673	.0603 to .0747	.0623 to .0723	2.812
16	0.0598	.0528 to .0668	.0548 to .0648	2.5
17	0.0538	.0478 to .0598	.0498 to .0578	2.25
18	0.04780438 to .0518	2
19	0.04180378 to .0458	1.75
20	0.03590329 to .0389	1.5
21	0.03290299 to .0359	1.375
22	0.02990269 to .0329	1.25
23	0.02690239 to .0299	1.125
24	0.02390209 to .0269	1
25	0.02090179 to .0239	0.875
26	0.01790159 to .0199	0.75
27	0.01640144 to .0184	0.688
28	0.01490129 to .0169	0.625
29	0.0135	0.562
30	0.012	0.5